

# **The Flow and Fracture of Cracked Ice: Experiments to Aid Modeling**

Dr. Erland M. Schulson  
Thayer School of Engineering  
Dartmouth College  
Hanover, NH 03755

Phone: 603-646-2888 Fax: 603-646-3856 Email: [erland.schulson@dartmouth.edu](mailto:erland.schulson@dartmouth.edu)

Grant No. N00014-97-1-0211

## **LONG TERM GOALS**

The ultimate goal of this work is to contribute new physical insight to the development of the next generation sea ice model, "PIPS 3.0". More specifically, it is to understand the processes underlying the deformation of first-year sea ice covers, from the formation of oriented leads to the frictional sliding of individual floes.

## **OBJECTIVE**

The objective is to test the hypothesis that first-year sea ice covers deform through a combination of continuum and granular flow. It is suggested that continuum flow controls deformation until "slip lines" develop, at which point granular flow governs. With this in mind, the near-term objectives are to study and understand the mechanical behavior of columnar sea ice deformed in the laboratory under controlled conditions and then to compare behavior on the small scale with that on the large scale. The second hypothesis to be tested is that the physical processes underlying the compressive failure of ice are independent of spatial scale.

## **APPROACH**

Deformation experiments on both the laboratory (sub-meter) and the intermediate/engineering (meter) scales are underway. A study is being made of the mechanical behavior of meter-sized blocks of ice grown under natural conditions and of the behavior of smaller specimens harvested from the larger blocks. The material is characterized by columnar grains whose crystallographic c-axes are randomly oriented within the plane of the sheet, as in natural first-year sea ice covers. The blocks are being loaded under compression at controlled strain rates. The experiments are being performed using a novel loading frame installed outdoors in a pond at USA-CRREL. In parallel with the lab experiments, satellite images of the sea ice cover are being examined for lead patterns. Also, in collaboration with W. D. Hibler, III models of the failure process are being developed.

## **WORK COMPLETED**

A second set of experiments using the outdoor facility was completed during the winter of '99, plus a comparative set of lab experiments on the compressive failure of material from the same source. Within the experimental scatter, there is no evidence of an effect of specimen size on either the ductile or the brittle compressive failure stress of S2 saline ice, at least over the range of size from ~0.1 to 1 meter. The work is being prepared for publication.

Report Documentation Page			Form Approved OMB No. 0704-0188		
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE <b>30 SEP 1999</b>		2. REPORT TYPE		3. DATES COVERED <b>00-00-1999 to 00-00-1999</b>	
4. TITLE AND SUBTITLE <b>The Flow and Fracture of Cracked Ice: Experiments to Aid Modeling</b>				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) <b>Dartmouth College,Thayer School of Engineering,Hanover,NH,03755</b>				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT <b>Approved for public release; distribution unlimited</b>					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT <b>Same as Report (SAR)</b>	18. NUMBER OF PAGES <b>3</b>	19a. NAME OF RESPONSIBLE PERSON
a. REPORT <b>unclassified</b>	b. ABSTRACT <b>unclassified</b>	c. THIS PAGE <b>unclassified</b>			

A preliminary examination of satellite images has extended the view, first expressed by Schulson and Hibler (1991) following observations of wing-like cracks in the ice cover of the Beaufort Sea, that the physics of failure may be independent of spatial scale. The observations are being included in a review paper on the brittle failure of ice currently in preparation by the author.

In collaboration with W. D. Hibler, III work has been completed on the development of an anisotropic sea ice model to describe the formation of oriented leads or "slip lines". A manuscript has been accepted for publication in Journal of Geophysical Research.

## RESULTS

Twelve additional experiments (totaling 26) were performed in the CRREL pond on 0.16 m thick blocks one meter on edge loaded under uniaxial compression at strain rates from  $10^{-5} \text{ s}^{-1}$  to  $10^{-2} \text{ s}^{-1}$  at temperatures close to the melting point. Also, 15 experiments were performed in the laboratory on cubes 0.15 m on edge, harvested from the same source and deformed at essentially the same temperature ( $\sim -3^\circ\text{C}$ ) and over the same range of strain rate. The experiments confirmed that independent of size the ductile-brittle transition occurred at a strain rate of  $10^{-3} \text{ s}^{-1}$ . Analysis of the complete set of ductile compressive strengths showed strain rate sensitivity  $m=0.19$  ( $\sigma \propto \dot{\epsilon}^m$ ), in reasonable agreement with values obtained from smaller specimens and with the literature (Kuehn and Schulson, 1994; Timco and Frederking 1986). The results offer no evidence for an effect of size per se on either the ductile or brittle compressive failure of saline ice, over the range investigated.

In addition to features (Schulson and Hibler 1991) that resemble wing cracks generated in the laboratory, satellite images reveal sets of interesting leads (e.g., Figure 2 of Marko and Thomson 1977; Figure 2 of Kwok et al. 1999) that resemble small-scale brittle compressive shear faults (Figure 2 of Schulson et al. 1999) plus crack patterns (e.g., Figure 7 of Erlingsson 1988) that resemble comb cracks generated in the laboratory (Figure 2 of Schulson et al. 1999). The in-pack stress (compressive) under which the field features may have formed was estimated from wing crack and comb crack mechanics to be between  $\sim 3$  and 30 kPa. This estimate is similar in magnitude to the range of in-pack compressive stress (10 to 100 kPa) measured by Coon et al. (1989), by Tucker and Perovich (1992) and by Richter-Menge and Elder (1998). The field stresses are about three orders of magnitude lower than failure stresses in the laboratory because the brittle compressive failure stress scales as  $\lambda^{-0.5}$ , where  $\lambda$  is the length of the stress concentrator and the concentrators in the field (thermal cracks, refrozen leads) are about six orders of magnitude larger than in the lab (i.e., km vs mm). The "look alike" features plus the rationalization of the failure stresses suggest that the physics of failure are scale independent. Supporting this suggestion are the results of a recent fractal analysis by Weiss (1999) of the fracture and fragmentation of ice on over nine orders of magnitude of spatial scale ( $10^{-4}$  to  $10^5 \text{ m}$ ).

## IMPACT/APPLICATIONS

As noted in Progress Report '98, the results are impacting the development of the numerical modeling of the flow and fracture of anisotropic sea ice and of lead formation. With "PIPS 3.0" in mind, collaboration continues with W.D. Hibler, III and has been initiated with J. Richter-Menge and J. Overland.

## TRANSITIONS

The foregoing results were presented during a PIPS 3.0 Development Team Meeting, National/Naval Ice Center, Washington, July 14-15, 1999.

## RELATED PROJECTS

Closely related to this project is one by W.D. Hibler under a separate ONR grant N00014-97-1-0381. He is numerically modeling the fracture and flow of anisotropic (cracked) sea ice.

## REFERENCES

- M. Coon et al. 1989. The architecture of an anisotropic elastic-plastic sea ice mechanics constitutive law. *Journal of Geophysical Research*. (103): p. 21915-21925.
- B. Erlingsson. 1988. Two-dimensional deformation patterns in sea ice. *Journal of Glaciology*. 34: 301-308.
- G. Kuehn and E. Schulson. 1994. Ductile Saline Ice. *Journal of Glaciology*. 40(136): 566-568.
- R. Kwok et al. in EOS. 1999. pp. 494 and 497.
- J. Marko and R. Thomson. 1977. Rectilinear Leads and Internal Motions in the Ice Pack of the Western Arctic Ocean. *Journal of Geophysical Research*. 82:979-987.
- J. Richter-Menge and B. Elder. 1998. Characteristics of pack ice stress in the Alaskan Beaufort Sea. *J. Geophys. Res.-Oceans*. 103(C10): 21817-21829.
- E. Schulson and W. Hibler. 1991. The fracture of ice on scales large and small: Arctic leads and wing cracks. *Journal of Glaciology*. 37(127): 319-323.
- E. Schulson, D. Iliescu and C. Renshaw. 1999. On the initiation of shear faults during brittle compressive failure: A new mechanism. *Journal of Geophysical Research*. 104(B1): 695-705.
- G. Timco and R. Frederking. 1986. Confined Compression Tests: Outlining the Failure Envelope of Columnar Sea Ice. *Cold Reg. Sci. Tech*. 12: 13-28.
- W. Tucker and D. Perovich. 1992. Stress measurements in drifting pack ice. *Cold Regions Science and Technology*. 20(2): 119-139.
- J. Weiss. 1999. Fracture and fragmentation of ice. *Engineering Fracture Mechanics* (submitted).

## PUBLICATIONS

- Schulson, E., Iliescu, D. and Renshaw, C. 1999: On the initiation of shear faults during brittle compressive failure: A new mechanism, *Journal Geophysical Research*, 104, 695-705.
- Schulson, E. 1999: The Structure and Mechanical Behavior of Ice, *Journal of Materials*, Feb., 21-27.
- Schulson, E. and Gratz, E. 1999: The brittle compressive failure of orthotropic ice under triaxial loading, *Acta mater.*, 47, 745-755
- Hibler, W. III, and Schulson, E. On modeling the anisotropic failure and flow of flawed sea ice, *Journal Geophysical Research* (in press).
- Weiss, J. and Schulson, E. Grain boundary sliding and crack nucleation in ice, *Phil. Mag.* (in press)
- Kennedy, F., Schulson, E. and Jones, D. Friction of ice on ice at low sliding velocities, *Phil. Mag.* (in press).
- Schulson, E. Ice: Mechanical Properties", *Encyclopedia of Materials Science and Engineering*, Pergamon Press (in press).
- Schulson, E., Swainson, I., Holden, T. and Korhonen, C. Ice Ih in hardened cement, *Cement and Concrete Research* (in press).